




CITGO HyDurance® AW NZ Fluids

OVERVIEW



- High-performance lubricants formulated with premium base stocks and ashless additives to provide outstanding protection for demanding hydraulic systems, especially those operating in environmentally sensitive areas.
- Zinc-free; zinc compounds are regulated as priority pollutants under provisions of the Clean Water Act and SARA Title 313.

FEATURES & BENEFITS




- Non-toxic in acute aquatic toxicity test (LC- 50) per OECD TG 203 limit test.
- Inherently biodegradable.
- Zinc-free formulation for less impact on the environment.
- Excellent thermal stability to virtually eliminate heat-related sludge deposits.
- Provide outstanding rust and corrosion protection.
- Separate readily from water.
- Contain inhibitors to minimize foaming and air entrainment.
- Provide premium anti-wear protection to pumps, motors, and other hydraulic components.
- Offer extended fluid service life capability with a fortified premium formulation to handle severe operating conditions.




CITGO HyDurance AW
NZ 32 Fluid

APPLICATIONS



- Recommended for premium non-zinc, anti-wear protection to vane, piston, and gear pumps, motors, valves, and other hydraulic circuit components when used in accordance with manufacturer's recommendations.
- Can be used in circulating systems of machine tools, presses, air compressors, and other gear and bearing applications where rust- and oxidation-inhibited oils are required.
- Meet or exceed the stringent performance requirements of:

GM LS-2	Fives Cincinnati P-68, P-69, P-70
Eaton Brochure 03-401-2010	U.S. Steel 127, 136, 126
DIN 51524 PART 2	Parker Denison HF-0
- Can be used in applications operating in environmentally sensitive areas where the use of a zinc-free, ashless formulated fluid is desired, such as:
 - Marine – offshore rigs, tugs, dredges, hydraulic lifts, cranes, pile-drivers (note: does not meet EPA 2013 Vessel General Permit VGP EAL requirements).
 - Forestry – scalpers, excavators, wheel loaders.
 - Construction – bulldozers, graders, backhoes.
 - Mining – conveyors, crawlers, hole drillers

PROPERTIES**Typical Properties for CITGO HyDurance AW NZ Fluids:**

Grade	32	46	68
Material Code	633615001	633616001	633617001
Gravity, ASTM D4052, °API	32.3	31.2	29.3
Density, lb/gal	7.19	7.24	7.33
Flash Point, ASTM D92 (COC), °C (°F)	215 (419)	206 (403)	242 (468)
Viscosity			
cSt at 40°C	32	46	68
cSt at 100°C	5.5	6.9	8.5
Viscosity Index, ASTM D2270	110	105	94
Pour Point ASTM D97, °C (°F)	-39 (-38)	-36 (33)	-24 (-11)
Color, ASTM D1500	L1.0	L1.0	L1.5
Total Acid No., ASTM D664, mgKOH/g	0.10	0.5	0.10
Copper Corrosion, ASTM D130, 3h at 100°C	1A	1A	1A
Rust Test, ASTM D665 A, B	Pass	Pass	Pass
Four Ball Wear, ASTM D4172, at 40 kg, mm	0.70	0.55	0.50
Foam Test, Seq. I, ml	20-0	0-0	0-0
Seq. II, ml	10-0	0-0	20-0
Seq. III, ml	20-0	0-0	0-0
Water Separability, ASTM D1401, at 130°F	40-40-0	40-40-0	40-40-0

CITGO and HyDurance are registered trademarks of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.